

Terlux 2802

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

TECHNICAL DATASHEET

DESCRIPTION

Terlux® 2802 is a standard injection molding grade based on a MABS polymer. Terlux® 2802 offers an unique combination of properties, such as a balanced stiffness/toughness ratio and the high transparency well known in SAN molding compositions.

FEATURES

- Excellent transparency
- Good resistance to chemicals
- Good stiffness and surface finish
- High impact strength

APPLICATIONS

- Cosmetic packaging
- Homeware
- Housings
- Toys, sport and leisure

| Property, Test Condition | Standard | Unit | Values |
|--|-------------|-------------------------|--------|
| Rheological Properties | | | |
| Melt Volume Rate 220 °C/10 kg | ISO 1133 | cm ³ /10 min | 2 |
| Melt Volume Rate, 220 °C/21.6 kg | ISO 1133 | cm ³ /10 min | 17 |
| Mechanical Properties | | | |
| Charpy Notched Impact Strength, 23° C | ISO 179/1eA | kJ/m ² | 5 |
| Charpy Notched Impact Strength, -30 °C | ISO 179/1eA | kJ/m ² | 2 |
| Charpy Unnotched, 23 °C | ISO 179/1eU | kJ/m ² | 120 |
| Charpy Unnotched, -30 °C | ISO 179/1eU | kJ/m ² | 80 |
| Tensile Stress at Yield, 23 °C | ISO 527 | MPa | 48 |
| Tensile Strain at Yield, 23 °C | ISO 527 | % | 4 |
| Tensile Modulus | ISO 527 | MPa | 2000 |
| Tensile Creep Modulus (1000h) | ISO 899 | MPa | 1250 |
| Nominal Strain at Break, 23 °C | ISO 527 | % | 12 |
| Flexural Strength, 23 °C | ISO 178 | MPa | 70 |
| Hardness, Ball Indentation | ISO 2039-1 | MPa | 70 |
| Thermal Properties | | | |
| Vicat Softening Temperature VST/B/50 (50N, 50 °C/h) | ISO 306 | °C | 93 |
| Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h) | ISO 306 | °C | 105 |

Terlux 2802

Methyl Methacrylate Acrylonitrile Butadiene Styrene (MABS)

TECHNICAL DATASHEET

| Property, Test Condition | Standard | Unit | Values |
|---|-------------|----------------------|------------------|
| Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa) | ISO 75 | °C | 90 |
| Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa) | ISO 75 | °C | 94 |
| Coefficient of Linear Thermal Expansion | ISO 11359 | 10 ⁻⁶ /°C | 80 - 110 |
| Thermal Conductivity | DIN 52612-1 | W/(m K) | 0.17 |
| Electrical Properties | | | |
| Dielectric Constant (100 Hz) | IEC 60250 | - | 2.9 |
| Dissipation Factor (100 Hz) | IEC 60250 | 10 ⁻⁴ | 160 |
| Dissipation Factor (1 MHz) | IEC 60250 | 10 ⁻⁴ | 140 |
| Volume Resistivity | IEC 60093 | Ohm*m | 10 ¹³ |
| Surface Resistivity | IEC 60093 | Ohm | 10 ¹⁵ |
| Optical Properties | | | |
| Refractive Index, Sodium D Line | ISO 489 | - | 1.54 |
| Other Properties | | | |
| Density | ISO 1183 | kg/m ³ | 1080 |
| Bulk Density (with external lubricant) | - | kg/m ³ | 590 |
| Water Absorption, Saturated at 23 °C | ISO 62 | % | 0.7 |
| Processing | | | |
| Linear Mold Shrinkage | ISO 294-4 | % | 0.4 - 0.7 |
| Mold Temperature Range | ISO 294 | °C | 50 - 75 |
| Injection Velocity | ISO 294 | mm/s | 200 |
| Drying Temperature | - | °C | 70 |
| Drying Time | - | h | 2 |

Typical values for uncolored products

SUPPLY FORM

Terlux® is supplied as lenticular and as cylindrical pellets. The bulk density is from about 0.55-0.65 g/cm³.

PROCESSING

Terlux is primarily processed through injection molding but any process suitable for thermoplastic molding compositions may also be used.

DISCLAIMER

The aforementioned data shall constitute the agreed contractual quality of the product sold by INEOS Styrolution at the time of passing of risk. INEOS Styrolution does not make any further warranty, representation or guarantee of any kind, express or implied, regarding the suitability of the product for any particular purpose or application and INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.
